

HELAVIA® sleeves - British norm in polychloroprene rubber for SES® sleeve process



HELAVIA®



HELAVIA

Material: polychloroprene rubber quality 3490
Operating temperatures: -30 to +90°C (+110°C short time)
Hardness shore A: 40 ±5
Tensile strength at break: >6,5 MPa
Ultimate elongation: >500 %
Tear strength: >10 kN/m
Dielectric strength: >13 kV/mm
Volume resistivity: 4x10⁹ Ω.cm
Flame resistance: V0 UL94
Specifications: British norm BS 3858 type 1C
Lubricated sleeves: all types



Standard colour: **010**
black

type	artide number length 20 mm	artide number length 25 mm	for wires Ø (mm)	Ø int. mm	wall mm	
A0a-M	0201 0611 010	0201 0612 010	1,2 - 2,5	1,2	0,75	1000
A0a-C	0201 0601 010	0201 0602 010				100
A0bis-M	0201 0613 010	0201 0614 010	1,5 - 3	1,5	0,75	1000
A0bis-C	0201 0603 010	0201 0604 010				100
A1a-M	0201 0615 010	0201 0616 010	2 - 4	2	0,75	1000
A1a-C	0201 0605 010	0201 0606 010				100
A2a-M	0201 0617 010	0201 0618 010	3 - 6	3	0,75	1000
A2a-C	0201 0607 010	0201 0608 010				100
A3a-M	-	0201 0619 010	5 - 10	5	1	1000
A3a-C	-	0201 0609 010				100



Standard colours:



Example for order:

code group	detail article	code colours
02010	xxxx	xxxx

type	artide number length 20 mm	artide number length 25 mm	for wires Ø (mm)	Ø int. mm	wall mm	
A0a-M COLOR	0201 0611 ***	0201 0612 ***	1,2 - 2,5	1,2	0,75	1000
A0a-C COLOR	0201 0601 ***	0201 0602 ***				100
A0bis-M COLOR	0201 0613 ***	0201 0614 ***	1,5 - 3	1,5	0,75	1000
A0bis-C COLOR	0201 0603 ***	0201 0604 ***				100
A1a-M COLOR	0201 0615 ***	0201 0616 ***	2 - 4	2	0,75	1000
A1a-C COLOR	0201 0605 ***	0201 0606 ***				100
A2a-M COLOR	0201 0617 ***	0201 0618 ***	3 - 6	3	0,75	1000
A2a-C COLOR	0201 0607 ***	0201 0608 ***				100
A3a-M COLOR	-	0201 0619 ***	5 - 10	5	1	1000
A3a-C COLOR	-	0201 0609 ***				100

